

## **Claim(s)**

**The invention is claimed as follows:**

(1) A roll of roofing membrane composed of non-woven fiberglass scrim covered and saturated with silicone rubber sealant on the top surface to a depth of 1/10 to 9/10 of the way into the thickness of the scrim and covered and saturated with pressure sensitive adhesive on the bottom or underside surface to the remaining 9/10 to 1/10 of the scrim's thickness.

(2) The invention recited in Claim (1) wherein the pressure sensitive adhesive is acrylic having a Tg from about -40C to -50C.

(3) The invention recited in Claim (1) wherein the fiberglass scrim is from about 0.010 inches to 0.040 inches thick.